

Panasonic Electric Works Electronic Materials Europe GmbH Specification Sheet

Specification sheet #

IPC-4101B/97

Reinforcement

1: Woven E-Glass

2: N/A

Resin System:

Primary: Difunctional Epoxy

Secondary 1: Multifunctional Epoxy

Secondary 2: N/A

Flam retardant mechanism

Bromine

Minimum UL94 Requirement: V0

Fillers:

Inorganic fillers

ID Reverence:

UL/ANSI: FR-4

Mil-S-13949: /04-GF,GFN,GFK,GFP,GFM

ANSI: FR4 / 97

Glass transition (TG):

110°C -150°C

Product name	Laminate: R-1755C	Prepreg: R-1650C
UL - Designation	R-1755C	R-1650C

1. Laminate		IPC Specification < 0, 5mm	IPC Specification >= 0, 5mm	Units	Typical Values < 0, 5mm	Typical Values >= 0, 5mm	Methode IPC-TM-650 (or as noted)
Physical Property							
Peel strength, minimum							
A: Low profile and very low profile copper foil, all copper foils > 18µm	18µm	0,7	0,7	N/mm	-	-	2.4.8 2.4.8.2 2.4.8.3
B: Standard profile copper foil	35µm	-	-		-	-	
1. after thermal stress		0,8	1,05		1,5	1,6	
2. at 125°C		0,7	0,7		1,4	1,5	
3. after process solutions		0,55	0,8		1,5	1,6	
Moisture Absorptions, maximum		-	0,8	%	-	0,09	2.6.2.1
Flexural strength, minimum	A: Length direction	-	415	N/mm2	-	595	2.4.4
	B: Cross direction	-	345		-	412	
Flammability (Laminate and prepreg as laminated)		V0 min	V0 min	Rating	V0	V0	UL 94
CTE (pre / post Tg)							
Z		-	-	ppm/°C	-	48/260	2.4.24
X		-	-		-	13	
Y		-	-		-	15	
T260 (TMA)	copper removed	-	30 min.	minutes	-	>120	2.4.24.1
T288 / T300 (TMA)	copper removed	-	5 min.	minutes	-	35 / NA	2.4.24.1
Density		-	-	g/cm3	1,93	1,93	
Decomposition Temperature		-	310 min.	°C	-	364	TGA
Electrical Property							
Volume resistivity, minimum	A: 96 / 35 / 90	1,0 E+06	-	MOhm-cm	5 E+07	-	2.5.17.1
	B: after moisture resistance	-	1,0 E+06		-	N/A	
	C: at elevated temp. E-24/125	1,0 E+03	1,0 E+03		N/A	N/A	
Surface resistivity, minimum	A: 96 / 35 / 90	1,0 E+04	-	MOhm	5,0 E+08	-	2.5.17.1
	B: after moisture resistance	-	1,0 E+04		-	N/A	
	C: at elevated temp. E-24/125	1,0 E+03	1,0 E+03		N/A	N/A	
Dielectric breakdown, minimum		-	40	kV	-	> 50	2.5.6
Permittivity, maximum (laminate and prepreg as laminated)	at 1 MHz	5,4	5,4	-	N/A	4,82	2.5.5.2/3/9
	at 1 GHz	-	-	-	N/A	4,38	
Loss tangent, maximum (laminate and prepreg as laminated)	at 1 MHz	0,035	0,035	-	0,015	0,015	2.5.5.2/3/9
	at 1 GHz	-	-	-	0,017	0,017	
Arc resistance, minimum		60	60	sec	NI	NI	2.5.1
Electrical strength, minimum (laminated and prepreg as laminated)		30	-	kV/mm	56	-	2.5.6.2
CTI (comparative tracking index)		-	-	V	-	200	IEC 112
Thermal Property							
Thermal stress 10 sec at 288°C, minimum	A: unetched	Pass	Pass	Rating	Pass	Pass	2.4.13.1
	B: etched	Pass	Pass		Pass	Pass	
Tg by DSC (TMA / DMA)		110min	110min	°C	135,2	135(135/155)	2.4.25
Thermal conductivity		-	-	W/mK	-	0,48	Laser flash
Specific heat		-	-	J/kgK	-	915	DSC
2. Prepreg Property		IPC-Specification		Units	Typical Values		
Shelf life, minimum (from date of delivery)	A: Condition <20°C, rel. H. <50%	90		Days	meets requirements		AABUS
	B: Condition < 5°C	180			meets requirements		
Volatile content, maximum		0,75		%	< 0,3		2.3.19
Prepreg parameters		-	-	-	AABUS		AABUS

AABUS= As agreed between user and supplier

Note:

Text data contained in this data sheet represents typical values and does not constitute any warranty or guarantee. For review of critical specification tolerances, please contact a Panasonic Electric Works representative. Panasonic Electric Works reserve the right to change these typical values as a natural process of refining our test equipment and technics.